



79 0734

Synthetic Waterproof Grease With PPTFE and Molybdenum

CHARACTERISTICS:

- Multi-purpose, all-weather lubricant:
- Year-round use
- Stability at high and low temperatures
- Non-melting:
- Resistant to extreme temperatures (-40°C/-40°F to 260°C/500°F)
- Is virtually waterproof:
- Will adhere where other greases do not
- Highly resistant to rust and corrosion
- Formulated with Teflon®,
- Will withstand extreme pressure caused by heavy loads and high speeds

FOR USE IN:

- **Automotive** – trucks, buses, trailers, skidoos
- **Farm equipment** – tractors, bailers, pickers
- **Construction** – bulldozers, cranes, back loaders
- **Forests and mines** – skidders, conveyors, saws
- **Food processing industry** (ovens, conveyors)
- **Fur and Leather tanneries** – tumblers, rollers
- **Marine and Fishing Industry** (canning, propellers)
- **Textile mills and dyeing** – dryers, jets, frames
- **Pulp and Paper mills** – conveyors, rollers, “wet end”
- **Foundries** – rolling and drawing equipment – cranes

Xp Lab, Inc.

946 W. HAWTHORN ST. SAN DIEGO, CA 92101

TEL. (619) 233-3111 FAX: (619)233-3112

Xp3@xplab.com

<http://www.xplab.com>

7/31/06



PHYSICAL PROPERTIES

79-0734	02	40	41	42	43	62
NLGI Grade	2	0	1	2	3	1.5
Melting Point °C	None	None	None	None	None	None
Dropping Point °C	None	None	None	None	None	None
Oil Separation (24Hrs a 25°C)	4%	4%	4%	4%	4%	4%
Penetration	270	355	325	265	240	285
After 60 Strokes	285	370	331	268	240	291
After 10,000 Strokes	290	375	335	273	247	310
After 60,000 Strokes	290	377	343	275	255	320
Copper Strip Test @163 °C 3 Hrs	Negative	Negative	Negative	Negative	Negative	Negative
Timken OK Load (kg)	45 +	45 +	45 +	45 +	45 +	45 +
Viscosity of Base Oil cSt @40°C cSt	220	190	220	220	220	220
@100° C cSt	24	32	32	32	32	8
Maximum Temperature en °C	215	270	270	270	270	215
Minimum Temperature en °C	-40	-40	-40	-30	-15	-54

Xp Lab, Inc.

946 W. HAWTHORN ST. SAN DIEGO, CA 92101

TEL. (619) 233-3111 FAX: (619)233-3112

Xp3@xplab.com

<http://www.xplab.com>